

Mipa 2K-HS-Löser-Spray

Item no 21254 0000

Technical data sheet

mipa

Professional Coating Systems

page 1 / 2

Intended use

Mipa 2K-HS-Löser-Spray is a special mixture of solvents (fade-out thinner) dissolve the overspray and to fade out the edges created during spot repair and blendings with Mipa 2K-HS-topcoats and clearcoat systems. Mipa 2K-HS-Löser-Spray can also be used as fade-out thinner for the following products:

Mipa PUR HS, Mipa OC, Mipa 2K-MS-Klarlacke, Mipa 2K-HS-Klarlacke.

Processing instructions



Substrates

-

Pre-treatment / cleansing



-

Characteristics

Very good dissolving properties
Ensures smooth transition zones when blending
Perfectly suitable for spot repairs
Homogeneous spray result
Reduces or even avoids polishing work

Colour / gloss level

Colourless



Preparation

Before use, shake can vigorously for 1 - 2 minutes!

Do not subject the can to high mechanical stress!

Application

Spray to test - spray distance approx. 20 - 30 cm

Flash-off time

-

After use

After use, turn can upside down and spray until the valve is clean.

Version: en 0126

This technical data sheet is supplied for informational purposes only! According to our information, all data and recommendations correspond to the state of art and are based on years of experience in manufacturing our products. They do not exempt the user from his obligation to verify professionally, on his own responsibility, the suitability of our products to the intended purpose under prevailing conditions. Safety data sheets and warnings on packaging must be observed. We reserve the right to modify and to complete the information content at any time, without prior notice or obligation to update.

MIPA SE · Am Oberen Moos 1 · D-84051 Essenbach · Tel.: +49 8703 92 20 · Fax: +49 8703 92 21 00 · mipa@mipa-paints.com · www.mipa-paints.com

Processing conditions From +10 °C and up to 80 % relative humidity. Ensure adequate air ventilation.

Storage Can be stored for 2 years in cool and dry places.

VOC-regulation EU limit value for the product (cat. B/e): 840 g/l
This product contains max. 800 g/l of VOC.

Safety information See safety data sheet

Processing instructions

Do not use on thermoplastic substrates.

Immediately after the painting process, spray Mipa 2K-HS-Löser-Spray on to the transition zones (overspray areas).

Apply Mipa 2K-HS-Löser-Spray only in thin, even coats until the rough overspray areas are visibly smoothed out.

Do not apply too thick a coat, as this will result in runners or uneven dissolving.