


### Intended use

2K polyurethane acrylic paint with long open time for the top quality coating of facades, machines and constructions. Suitable for brush and roller applications.

This product complies in combination with EP 100-20 with the requirements for fire behaviour of materials and components according to EN 45545-2:2013 + A1:2015.

### Processing instructions



#### Mixing ratio

##### hardener

PU 900-25, PU 912-XX, H-XX  
PU 933-10, PU 950-25

##### by weight (lacquer : hardener)

5 : 1

##### by volume (lacquer : hardener)

4 : 1

PU 914-XX

8 : 1

6 : 1

PU 916-XX, A 60

10 : 1

8 : 1



#### Hardener

Mipa PU 900-25, PU 912-10, PU 912-25, PU 912-40, PU 933-10, PU 950-25, H-XX

Mipa PU 914-10, PU 914-25, PU 914-40

Mipa PU 916-10, PU 916-25

Mipa PUR Plus-Härter A 60



#### Pot life

with hardener -10 approx. 1,5 h at 20 °C

with hardener A 60 approx. 8 h at 20 °C



#### Thinner

Mipa 2K-Verdünnung V 10, V 25, V 40



#### Processing viscosity

##### gravity spray gun

20 - 25 s 4 mm DIN

##### Airmix/Airless

30 - 40 s 4 mm DIN



#### Application mode

##### application mode

gravity spray gun/  
HVLP

##### hardener

PU 900 / 912 /  
933 / 950

##### pressure (bar)

2,0 - 2,5

##### nozzle (mm)

1,2 - 1,3

##### spray passes

2 - 4

##### dilution

15 - 20 %

gravity spray gun/  
HVLP

PU 914 / 916

2,0 - 2,2

1,5 - 2,0

1 - 3

0 - 5 %

Airmix / Airless  
compound pressure

PU 900 / 912 /  
933 / 950

1,0 - 2,0  
100 - 120

0,23 - 0,28

1

0 - 10 %

Airmix / Airless  
compound pressure

PU 914 / 916

1,0 - 2,0  
100 - 120

0,23 - 0,28

1

0 - 5 %

brush, roller\*


A 60

–

–

–

0 - 5 %

	Drying time						
	hardener	object temperature	dust dry	set to touch	ready for assembly	sandable	recoatable
	-10	20 °C	15 - 30 min	2 - 3 h	12 h	--	--
	-10	60 °C	--	20 min	30 - 40 min	--	--
	-25	20 °C	30 - 45 min	3 - 4 h	16 h	--	--
	-25	60 °C	--	30 min	45 min	--	--
	-40 / A 60	20 °C	1,5 - 2 h	8 - 10 h	24 h	--	--
	-40 / A 60	60 °C	--	--	1 h	--	--
	PU 933-10	20 °C	1,5 - 2 h	2 - 3 h	12 h	--	--

Fully cured after 7 - 8 days (20 °C).

### Note

#### Characteristics:

binder base: polyurethane-acrylic system  
 solids content (% by weight): ~ 76  
 solids content (% by volume): ~ 59  
 delivery viscosity DIN 53211 4 mm (in s): thixotropic  
 density DIN EN ISO 2811 (kg/l): ~ 1,5  
 gloss level ISO 2813 at 60° (GU): 20 - 30 satin matt

#### Properties:

Long open time, high-build coating  
 Electrostatic application possible  
 Highly resistant to water  
 Highly UV- and weather-resistant  
 Heat resistance:  
 - Short-term heat exposure: 180 °C  
 - Permanent heat exposure: 150 °C  
 Adhesion on steel, zinc substrates and glass  
 Adhesion on aluminium: Gt 1

#### Theoretical spreading rate:

~ 42,2 m<sup>2</sup>/kg, 10:1 by weight with A 60, for 10 µm dry film thickness.  
 ~ 60,6 m<sup>2</sup>/l, 10:1 by weight with A 60, for 10 µm dry film thickness.  
 ~ 36,9 m<sup>2</sup>/kg, 5:1 by weight with PU 900-25, for 10 µm dry film thickness.  
 ~ 49,8 m<sup>2</sup>/l, 5:1 by weight with PU 900-25, for 10 µm dry film thickness.

#### Storage:

For at least 3 years in the unopened original container. Optimum storage conditions between + 5 °C and + 25 °C, avoid direct sunlight. Other storage conditions may lead to undesirable properties of the material.

#### VOC:

< 360 g/l\*\*

#### Processing conditions:

From + 10 °C and up to 80 % relative humidity. Ensure adequate air ventilation.

**Substrate preparation:** Remove oil, grease, rust, mill scale, rolling skins, as well as other substances impairing the function of the coating!

Attention: A direct adhesion cannot be taken as granted due to most different kinds of metals, alloys, metallic and conversion coatings and so on. The adhesion must therefore be tested on the original substrate.

Steel:

- Blast to cleaning degree Sa 2½, remove blast residues and overcoat promptly.
- De-rust with hand and power tools to degree of cleanliness St 3.
- Degrease with Mipa WBS Reiniger or Mipa Silikonentferner.

Zincd substrates:

- Clean the surface with the ammonia solution Mipa Zinkreiniger.
- Sweep blast.

Aluminium:

- Degrease with Mipa 2K-Verdünnung, sand thoroughly with sandpaper P 360/400 and clean subsequently with Mipa Silikonentferner.

Powder-coated and coil-coated facade elements:

- Preclean with Mipa WBS Reiniger, wash with water and clean again with Mipa Silikonentferner and in case of chalking old paintworks apply Mipa Tiefgrund LH to consolidate the substrate.

Glass:

1. Before coating, it is indispensable to determine definitely the recoatable glass surface (e.g. by means of an appropriate measure device to determine the tin side of float glass) because it is generally impossible to coat the side which came in contact with the tin bath.
2. Degrease with Mipa WBS Reiniger or Mipa Silikonentferner.

**Proposed coating structure:** Single coat system

Steel, zincd substrates, aluminium:  
PU 250-30 with 60 - 70 µm dry film thickness.

2-coat system

Steel, zincd substrates, aluminium:  
Priming coat: \*\*\*EP 100-20 with 50 - 70 µm dry film thickness or 25 - 30 µm dry film thickness on aluminum.  
Finishing coat: PU 250-30 with 50 - 60 µm dry film thickness.

Powder-coated or coil-coated facade elements:

Primer for spot repair: \*\*\*EP 100-20 with 50 - 70 µm dry film thickness.  
Finishing coat: PU 250-30 with 60 - 80 µm dry film thickness.

Glass:

Pretreatment: 1K-Glasprimer.  
Finishing coat: PU 250-30, incl. PU 950-25, with 50 - 60 µm dry film thickness.

Single coat system

Glass:  
PU 250-30, incl. PU 950-25, with 50 - 60 µm dry film thickness.

### Special notes:

\*Suitable: e.g. mohair, nap, velour, Glattfilt, Rolloplan, foam paint roller.

\*\*This product contains the following maximum VOC-values:

- Applied by brush/ roller with hardener Härter A 60: < 400 g/l of VOC.
- Applied by spraying with hardener PU 914-XX, PU 916-XX: < 420 g/l of VOC.
- Applied by spraying with hardener PU 900-25, PU 912-XX, PU 933-10, PU 950-25: < 500 g/l of VOC.

\*\*\*Further Mipa primers are available. Please contact your technical adviser or our application technicians.

For professional use only.

The details of the paragraphs - Proposed coating structure, Characteristics, Theoretical spreading rate, VOC - refer to the colour shade RAL 7035. For other colour shades, these may deviate.

Especially UV-resistant pigmentations (e.g. pastel shades for facades) are available on demand.

Furthermore it's possible to mix it with neon colours which can be applied then as single-layer. Please see the technical data sheet "Mipa Neon-Farbtöne PMI single-layer paints"

Check colour before use.

In case of application by means of an Airmix/Airless device, it is recommended testing beforehand the equipment for its suitability. If micro foam or blistering emerge during the application with an Airmix/Airless device, it is recommended adding more thinner or using the additives 2K-Systemzusatz PUA and PUS. Furthermore, the film thickness should be kept as low as possible.

Mipa PU 250-30 can also be applied on mineral substrates. Please observe technical data sheet Mipa PU 250-30 Fußbodenbeschichtung to get more information about application and properties.

If required we also offer hardeners and cleaning agents that are suitable for 2-component mixing and dosing units. Please contact your technical adviser or our application technicians.

Depending on the hardener in use and on the processing condition, the gloss level may prove to be higher or lower. The mentioned data refer to the hardener of series: PU 900-25, PU 912-XX, PU 933-10, PU 950-25.

### Cleaning of tools:

Clean tools immediately after use with Mipa Nitroverdünnung.